

Memtec MF 1.2

DESCRIPTION

Memtec MF 1.2 is a flexible PVC-P vinyl membrane which is 1.2 mm thick and is reinforced with a polyester mesh.

APPLICATIONS

Memtec MF 1.2 is suitable for waterproofing roofs, ballasted systems and mechanically-fastened system both in new construction and refurbishment.

PROPERTIES

- Memtec MF 1.2 meets the requirements of EN 13956 standard specification.
- Certificate CE no.0099/CPD/A85/0081.
- Membrane made exclusively from virgin resins.
- Extremely long-lasting.
- Highly puncture resistant.
- Excellent stability under UV radiation.
- Excellent mechanical properties.
- High resistance to laceration.
- Easily welded using hot air, even several years after installation.
- Can be recycled.
- Excellent flexibility at low temperatures.

INSTALLATION

- Memtec MF 1.2 waterproofing systems must be installed by experienced and qualified personnel.
- Surfaces must be clean and dry and free from sharp obtrusions. The membrane can be used on bituminous felt, asphalt and polystyrene insulation by using a suitable geotextile as a separating layer or Memtec fleece backed membrane type MF-FB.
- The membrane is laid flat without creases and fixed to the support surface.
- Membranes should be joined using hot air welding so giving a double-thickness seam for mechanical fixing.
- Before starting welding adjust the parameters for speed and temperature according to the ambient conditions and the surfaces of the membrane.

PACKAGING AND STORAGE

Colours	Light grey, Dark grey
Dimensions	2.10 x 20m (42m ² /Roll) 1.04 x 15m (15.6m ² /Roll)
Rolls/Pallet	18 – 15
Storage	Horizontally and in parallel (never crossed)

Supplied in rolls on cardboard tubing.
Store in the original packaging in a dry and cool place.

Memtec Limited
Unit A, Brightside
Westfield Sole Road
Boxley, Maidstone
Kent, ME14 3EH

Tel: 01634-869806
Fax: 01634-682436
Email: info@memtec.co.uk
Website: www.memtec.co.uk

MEMTEC
Modern
efficient
performance
cost effective
flat roofing
systems

Photo courtesy of ©Denne.

Memtec MF 1.2

Flexible PVC membrane with polyester reinforcement.
Dimensions 2.10m x 20m x 1.2mm – 1.04m x 15m x 1.2mm
Applications: mechanically-fastened system.

SPECIFICATIONS	Test method	Unit	Memtec MF 1.2
External fire behaviour	prEN 13501-5	-	Broof (t1), Broof (t3)
Reaction to fire	EN 13501-1:2002 (EN ISO 11925-2)	-	E
Watertightness	EN1928:2000 (B)	-	Pass
Tensile strength to Break	EN12311-2	N/50 mm	≥1100x1000
Elongation at Break	EN12311-2	%	≥20
Static puncture resistance	EN12730 (A)	kg	25
Impact resistance	EN12691	mm	≥500 (Hard substrate) ≥700 (Soft substrate)
Tear resistance	EN 12310-2	N	≥200
Joint separation resistance	EN12316-2	N/50mm	≥200
Joint shear resistance (L x T)	EN12317-2	N/50mm	≥1000x1000
Artificial aging due to prolonged Exposure to UV radiation,High Temperatures and water	EN1297	Visual	Pass
Flexibility under low temperatures	EN495-5	°C	≤-25

OTHER SPECIFICATIONS	Test method	Unit	Value
Visible defects	EN1850-2	-	Pass
Length	EN1848-2	m	20
Width	EN1848-2	m	2.1
Straightness	EN1848-2	mm	≤50
Mass per unit area	EN1849-2	kg/m ²	1.56
Thickness	EN1849-2	mm	1.2
Flatness	EN1848-2	mm	≤10
Dimensional stability	EN1107-2	%	≤0.3
Water vapour transmission properties	EN1931	μ	20.000

Memtec Limited reserves the right to modify information without prior warning and will not take responsibility for anomalies caused by incorrect use of the product. The values shown in the technical sheets are the average values resulting from tests carried out in our laboratory.

Memtec Limited
Unit A, Brightside
Westfield Sole Road
Boxley, Maidstone
Kent, ME14 3EH

Tel: 01634-869806
Fax: 01634-682436
Email: info@memtec.co.uk
Website: www.memtec.co.uk

